

PRODUCT DATA SHEET



AGILON66 30GF

Product Description

Polyamide 66- 30% Glass filled

Product Applications

Automotive, Electronics & Electrical ,Furniture ,Railways etc.

General

- Filler/Reinforcement - Glass fiber
- Forms - Pellets
- Appearance/Color - Black
- Processing Method - Injection molding

Physical	Typical Value	Unit	Test Method
Specific Gravity	1.35		ASTM D -792

Mechanical	DAM	Unit	Test Method
Tensile Strength	135	Mpa	ASTM D-638
Elongation at Break	6	%	ASTM D-638
Flexural strength	205	MPa	ASTM D-790
Flexural Modulus	8500	MPa	ASTM D-790
Notched Izod Impact strength	9	Kg.cm/cm	ASTM D-256A



PRODUCT DATA SHEET

AGILON66 30GF

Drying conditions

It is recommended to pre dry Nylon granules at 85-100 °C for 3-4 Hrs.
Moisture content after drying should be <0.2%.
Avoid sudden cooling of dry pellet.

Injection Molding conditions (° C)

Feed Zone	Centre	Nozzle	Melt	Mould
250-270	265-280	270-280	255-270	60-80

Note

All Properties measured at 23 Deg. / 50% RH on dry-as-moulded test specimens. Only typical data for material selection purposes only. Users have to establish material suitability. The information & data presented herein are to the best of our knowledge. No warranty or guarantee expressed or implied is made regarding performance. The information and data are subject to change without prior intimation based on research and development work undertaken by the company.

Plant

C-10/1,MIDC,AkkalkotRoad - 413006
Solapur,Maharashtra,India

Corporate Office

510 "A" Wing Kohinoor City Commercial –I, Kirol Road,
Off . L.B .S Marg,Kurla (W) Mumbai - 400070 ,India

