Corporate Office: 510, A Wing, Kohinoor City C-I Kirol Road, Off L.B.S. Marg, Kurla (W) Mumbai - 400 070, India T: +91 22 6708 2600 / 2500

F: +91 22 6708 2600 /



GRPLON055G

UNFILLED POLYAMIDE 6

GRPLON055G is an engineered polyamide 6. It is available in black color with good mechanical properties and melt flow during processing. It is suitable for making general purpose, automotive, industrial and consumer durable products by injection molding and extrusion process.

TECHNICAL DATASHEET

| Property | ASTM Standard | Unit | Specification |
|------------------------------|---------------|------|----------------|
| Tensile Strength | D 638 | MPa | 45 ± 5 |
| Elongation at Yield | D 638 | % | 4.0 ± 0.5 |
| Elongation at Break | D 638 | % | 5.0 ± 0.5 |
| Flexural Strength | D 790 | MPa | 45 ± 5 |
| Flexural Modulus | D 790 | MPa | 1900 ± 100 |
| Notched-Izod Impact Strength | D 256 | J/m | 45 ± 5 |

Typical Applications:

- Automotive, Industrial and Consumer products
- Blending resin with Nylon 6

The information & data presented herein are to the best of our knowledge. No warranty or guarantee expressed or implied is made regarding performance. The information and data are subject to change without prior intimation based on research and development work undertaken by the company.

www.grpweb.com

